MATERIAL DATA SHEET

Aluminum 2219-T87 sheet/plate, 3.2-25 mm (MIL-HDBK-5H)

Historical public-release A-basis 2219-T87 sheet and plate reference.

Field	Value
Material ID	milhdbk-2219-t87-sheet-plate-3-2-25-mm
Category	Metal
Condition	2219-T87; sheet or plate; 3.2-25 mm | sheet or plate
Unit system	Common SI
Unit contract	Material properties stored in SI engineering units.
Generated	2026-11-15 23:15

Source and Validity

Field	Value
Quality	Catalog record
Design release allowed	No
Source family	Government materials handbook
Confidence	Reference-grade
License	Open
Source note	Independent transcription from an official public-release U.S. government handbook.
Citation	U.S. Department of Defense, MIL-HDBK-5H, Metallic Materials and Elements for Aerospace Vehicle Structures, 1 December 1998, Table 3.2.7.0(b2)-(b3), PDF page(s) 463-464 (handbook page(s) 3-167 to 3-168); official DLA document record https://quicksearch.dla.mil/qsDocDetails.aspx?ident_number=53876. The official PDF carries Distribution Statement A: Approved for public release; distribution is unlimited.
Valid temperature	21 ... 21 degC (Room-temperature historical handbook values. Applicability is limited to the exact alloy, temper/condition, product form, size band, material axis, statistical basis, and specification identified by the cited table.)
Valid pressure	Pressure dependence is not represented by these solid-material reference values.
Valid phase / condition	2219-T87; sheet or plate; 3.2-25 mm
Uncertainty	Values are historical handbook table transcriptions with explicit SI conversion. They are not a substitute for a current material specification, supplier certificate, drawing allowable, or project approval.
Last reviewed	2026-08-02
Reviewer	scripts/import_milhdbk5h_public_metals.py
Review status	Checked

Field	Value
Review scope	Checked official DLA document identity, Distribution Statement A, PDF hash, table/page location, alloy/condition/form/size scope, basis semantics, and SI conversions.
Notes	Historical reference only; design release is explicitly disabled.
License ID	US-DOD-DISTRIBUTION-STATEMENT-A
License URL	https://www.dodcui.mil/Distribution-Statements/
Attribution	U.S. Department of Defense

Material Condition

Field	Value
Condition	2219-T87; sheet or plate; 3.2-25 mm
Temper	T87
Heat treatment	solution heat treated, cold worked and artificially aged
Product form	sheet or plate
Thickness / diameter range	0.126-0.984 in (3.2-25 mm), within the sheet/plate table bands
Test direction	L and LT
Processing route	wrought heat-treatable aluminum-copper sheet or plate
Temperature range	21 ... 21 degC
Notes	Room-temperature historical handbook values. Applicability is limited to the exact alloy, temper/condition, product form, size band, material axis, statistical basis, and specification identified by the cited table. Historical reference only; confirm the current procurement specification and material test report.

Properties

Physical

Property	Value	Unit	Type	Applies to
Density	2851	kg/m^3	Historical Nominal	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables

Mechanical

Property	Value	Unit	Type	Applies to
Ultimate tensile strength, L	434.37	MPa	Historical Public Release Table Value	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables; L direction
Tensile yield strength, L	344.738	MPa	Historical Public Release Table Value	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables; L direction
Ultimate tensile strength, LT	441.264	MPa	Historical Public Release Table Value	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables; LT direction
Tensile yield strength, LT	351.633	MPa	Historical Public Release Table Value	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables; LT direction
Compressive yield strength, L	351.633	MPa	Historical Public Release Table Value	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables; L direction
Compressive yield strength, LT	365.422	MPa	Historical Public Release Table Value	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables; LT direction
Ultimate shear strength	248.211	MPa	Historical Public Release Table Value	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables
Elongation, LT	5	%	Historical Public Release Table Value	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables; LT direction
Ramberg-Osgood exponent, tension L	14	-	Historical Public Release Table Value	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables; L direction; typical room-temperature curve; sheet/plate thickness 0.125-1.000 in
Ramberg-Osgood exponent, tension LT	14	-	Historical Public Release Table Value	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables; LT direction; typical room-temperature curve; sheet/plate thickness 0.125-1.000 in

Property	Value	Unit	Type	Applies to
Ramberg-Osgood exponent, compression L	14	-	Historical Public Release Table Value	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables; L direction; typical room-temperature curve; sheet/plate thickness 0.125-1.000 in
Ramberg-Osgood exponent, compression LT	14	-	Historical Public Release Table Value	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables; LT direction; typical room-temperature curve; sheet/plate thickness 0.125-1.000 in
Young's modulus	72.395	GPa	Historical Nominal	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables
Compression modulus	74.463	GPa	Historical Nominal	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables
Shear modulus	27.579	GPa	Historical Nominal	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables
Poisson's ratio	0.33	-	Historical Nominal	2219-T87; sheet or plate; 3.2-25 mm; lower A-basis value across sheet and plate tables

Engineering note: seed solid-material values are reference values only. Verify against the project material specification or supplier data sheet before release.