MATERIAL DATA SHEET

Aluminum 7050-T7452 hand forging, <=175 mm (MIL-HDBK-5H)

Historical public-release hand-forging reference conservatively combined through 175 mm.

Field	Value
Material ID	milhdbk-7050-t7452-hand-forging-175-mm
Category	Metal
Condition	7050-T7452; hand forging; <=175 mm thickness at heat treatment | hand forging
Unit system	Common SI
Unit contract	Material properties stored in SI engineering units.
Generated	2026-11-15 23:15

Source and Validity

Field	Value
Quality	Catalog record
Design release allowed	No
Source family	Government materials handbook
Confidence	Reference-grade
License	Open
Source note	Independent transcription from an official public-release U.S. government handbook.
Citation	U.S. Department of Defense, MIL-HDBK-5H, Metallic Materials and Elements for Aerospace Vehicle Structures, 1 December 1998, Table 3.7.3.0(d), PDF page(s) 609 (handbook page(s) 3-313); official DLA document record https://quicksearch.dla.mil/qsDocDetails.aspx?ident_number=53876. The official PDF carries Distribution Statement A: Approved for public release; distribution is unlimited.
Valid temperature	21 ... 21 degC (Room-temperature historical handbook values. Applicability is limited to the exact alloy, temper/condition, product form, size band, material axis, statistical basis, and specification identified by the cited table.)
Valid pressure	Pressure dependence is not represented by these solid-material reference values.
Valid phase / condition	7050-T7452; hand forging; <=175 mm thickness at heat treatment
Uncertainty	Values are historical handbook table transcriptions with explicit SI conversion. They are not a substitute for a current material specification, supplier certificate, drawing allowable, or project approval.
Last reviewed	2026-08-02
Reviewer	scripts/import_milhdbk5h_public_metals.py
Review status	Checked

Field	Value
Review scope	Checked official DLA document identity, Distribution Statement A, PDF hash, table/page location, alloy/condition/form/size scope, basis semantics, and SI conversions.
Notes	Historical reference only; design release is explicitly disabled.
License ID	US-DOD-DISTRIBUTION-STATEMENT-A
License URL	https://www.dodcui.mil/Distribution-Statements/
Attribution	U.S. Department of Defense

Material Condition

Field	Value
Condition	7050-T7452; hand forging; <=175 mm thickness at heat treatment
Temper	T7452
Heat treatment	solution heat treated, stress relieved and overaged to T74 condition
Product form	hand forging
Thickness / diameter range	<=6.890 in (175 mm), within the <=7.000 in table bands
Test direction	L, LT and ST where available; lower listed value across applicable size bands
Processing route	hand-forged heat-treatable aluminum-zinc alloy
Temperature range	21 ... 21 degC
Notes	Room-temperature historical handbook values. Applicability is limited to the exact alloy, temper/condition, product form, size band, material axis, statistical basis, and specification identified by the cited table. Historical reference only; confirm the current procurement specification and material test report.

Properties

Physical

Property	Value	Unit	Type	Applies to
Density	2823	kg/m^3	Historical Nominal	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in

Mechanical

Property	Value	Unit	Type	Applies to
Ultimate tensile strength, L	468.843	MPa	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; L direction
Tensile yield strength, L	386.106	MPa	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; L direction
Ultimate tensile strength, LT	461.949	MPa	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; LT direction
Tensile yield strength, LT	372.317	MPa	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; LT direction
Compressive yield strength, L	386.106	MPa	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; L direction
Compressive yield strength, LT	393.001	MPa	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; LT direction
Ultimate shear strength	275.79	MPa	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in
Elongation, L	9	%	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; L direction
Elongation, LT	4	%	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; LT direction

Property	Value	Unit	Type	Applies to
Ultimate tensile strength, ST	448.159	MPa	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; ST direction; available from 2.001 in and above
Tensile yield strength, ST	351.633	MPa	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; ST direction; available from 2.001 in and above
Compressive yield strength, ST	386.106	MPa	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; ST direction; available from 2.001 in and above
Elongation, ST	3	%	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; ST direction; available from 2.001 in and above
Ramberg-Osgood exponent, tension L	14	-	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; L direction; typical room-temperature curve; hand-forging thickness <=7.000 in
Ramberg-Osgood exponent, tension LT	14	-	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; LT direction; typical room-temperature curve; hand-forging thickness <=7.000 in
Ramberg-Osgood exponent, tension ST	9.3	-	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; ST direction; typical room-temperature curve; hand-forging thickness <=7.000 in

Property	Value	Unit	Type	Applies to
Ramberg-Osgood exponent, compression L	15	-	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; L direction; typical room-temperature curve; hand-forging thickness <=7.000 in
Ramberg-Osgood exponent, compression LT	18	-	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; LT direction; typical room-temperature curve; hand-forging thickness <=7.000 in
Ramberg-Osgood exponent, compression ST	20	-	Historical Public Release Table Value	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in; ST direction; typical room-temperature curve; hand-forging thickness <=7.000 in
Young's modulus	70.327	GPa	Historical Nominal	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in
Compression modulus	73.084	GPa	Historical Nominal	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in
Shear modulus	26.89	GPa	Historical Nominal	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in
Poisson's ratio	0.33	-	Historical Nominal	7050-T7452; hand forging; <=175 mm thickness at heat treatment; lower S/A-basis value across <=7.000 in

Engineering note: seed solid-material values are reference values only. Verify against the project material specification or supplier data sheet before release.