MATERIAL DATA SHEET

Aluminum 7149-T73 die forging, <=100 mm (MIL-HDBK-5H)

Historical public-release T73 die-forging reference through 100 mm heat-treatment thickness.

Field	Value
Material ID	milhdbk-7149-t73-die-forging-100-mm
Category	Metal
Condition	7149-T73; die forging; <=100 mm thickness at heat treatment | die forging
Unit system	Common SI
Unit contract	Material properties stored in SI engineering units.
Generated	2026-11-15 23:15

Source and Validity

Field	Value
Quality	Catalog record
Design release allowed	No
Source family	Government materials handbook
Confidence	Reference-grade
License	Open
Source note	Independent transcription from an official public-release U.S. government handbook.
Citation	U.S. Department of Defense, MIL-HDBK-5H, Metallic Materials and Elements for Aerospace Vehicle Structures, 1 December 1998, Table 3.7.2.0(c), PDF page(s) 587 (handbook page(s) 3-291); official DLA document record https://quicksearch.dla.mil/qsDocDetails.aspx?ident_number=53876. The official PDF carries Distribution Statement A: Approved for public release; distribution is unlimited.
Valid temperature	21 ... 21 degC (Room-temperature historical handbook values. Applicability is limited to the exact alloy, temper/condition, product form, size band, material axis, statistical basis, and specification identified by the cited table.)
Valid pressure	Pressure dependence is not represented by these solid-material reference values.
Valid phase / condition	7149-T73; die forging; <=100 mm thickness at heat treatment
Uncertainty	Values are historical handbook table transcriptions with explicit SI conversion. They are not a substitute for a current material specification, supplier certificate, drawing allowable, or project approval.
Last reviewed	2026-08-02
Reviewer	scripts/import_milhdbk5h_public_metals.py
Review status	Checked

Field	Value
Review scope	Checked official DLA document identity, Distribution Statement A, PDF hash, table/page location, alloy/condition/form/size scope, basis semantics, and SI conversions.
Notes	Historical reference only; design release is explicitly disabled.
License ID	US-DOD-DISTRIBUTION-STATEMENT-A
License URL	https://www.dodcui.mil/Distribution-Statements/
Attribution	U.S. Department of Defense

Material Condition

Field	Value
Condition	7149-T73; die forging; <=100 mm thickness at heat treatment
Temper	T73
Heat treatment	supplier heat treated and supplied in the T73 temper
Product form	die forging
Thickness / diameter range	<=3.937 in (100 mm), within the <=4.000 in table bands
Test direction	L, transverse-to-flow and ST as tabulated
Processing route	die-forged heat-treatable aluminum-zinc alloy
Temperature range	21 ... 21 degC
Notes	Room-temperature historical handbook values. Applicability is limited to the exact alloy, temper/condition, product form, size band, material axis, statistical basis, and specification identified by the cited table. Historical reference only; confirm the current procurement specification and material test report.

Properties

Physical

Property	Value	Unit	Type	Applies to
Density	2851	kg/m^3	Historical Nominal	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in

Mechanical

Property	Value	Unit	Type	Applies to
Ultimate tensile strength, L	468.843	MPa	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in; L direction
Tensile yield strength, L	393.001	MPa	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in; L direction
Compressive yield strength, L	406.791	MPa	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in; L direction
Ultimate shear strength	262.001	MPa	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in
Elongation, L	7	%	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in; L direction
Ultimate tensile strength, T	482.633	MPa	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in; T direction
Tensile yield strength, T	413.685	MPa	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in; T direction
Compressive yield strength, ST	365.422	MPa	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in; ST direction
Elongation, T	2	%	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in; T direction

Property	Value	Unit	Type	Applies to
Ramberg-Osgood exponent, tension L	54	-	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in; L direction; typical room-temperature curve; die-forging thickness <4.000 in
Ramberg-Osgood exponent, tension ST	29	-	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in; ST direction; typical room-temperature curve; die-forging thickness <4.000 in
Ramberg-Osgood exponent, compression L	54	-	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in; L direction; typical room-temperature curve; die-forging thickness <4.000 in
Ramberg-Osgood exponent, compression ST	29	-	Historical Public Release Table Value	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in; ST direction; typical room-temperature curve; die-forging thickness <4.000 in
Young's modulus	70.327	GPa	Historical Nominal	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in
Compression modulus	73.774	GPa	Historical Nominal	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in
Shear modulus	26.89	GPa	Historical Nominal	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in
Poisson's ratio	0.33	-	Historical Nominal	7149-T73; die forging; <=100 mm thickness at heat treatment; lower A-basis value across <=4.000 in

Engineering note: seed solid-material values are reference values only. Verify against the project material specification or supplier data sheet before release.