MATERIAL DATA SHEET

Ti-15V-3Cr-3Sn-3Al STA sheet, <=1.9 mm (MIL-HDBK-5H)

Historical public-release S-basis STA sheet reference through 1.9 mm.

Field	Value
Material ID	milhdbk-ti15v3cr3sn3al-sta-sheet-1-9-mm
Category	Metal
Condition	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm | sheet
Unit system	Common SI
Unit contract	Material properties stored in SI engineering units.
Generated	2026-11-15 23:02

Source and Validity

Field	Value
Quality	Catalog record
Design release allowed	No
Source family	Government materials handbook
Confidence	Reference-grade
License	Open
Source note	Independent transcription from an official public-release U.S. government handbook.
Citation	U.S. Department of Defense, MIL-HDBK-5H, Metallic Materials and Elements for Aerospace Vehicle Structures, 1 December 1998, Table 5.5.2.0(b), PDF page(s) 990 (handbook page(s) 5-130); official DLA document record https://quicksearch.dla.mil/qsDocDetails.aspx?ident_number=53876. The official PDF carries Distribution Statement A: Approved for public release; distribution is unlimited.
Valid temperature	21 ... 21 degC (Room-temperature historical handbook values. Applicability is limited to the exact alloy, temper/condition, product form, size band, material axis, statistical basis, and specification identified by the cited table.)
Valid pressure	Pressure dependence is not represented by these solid-material reference values.
Valid phase / condition	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm
Uncertainty	Values are historical handbook table transcriptions with explicit SI conversion. They are not a substitute for a current material specification, supplier certificate, drawing allowable, or project approval.
Last reviewed	2026-08-02
Reviewer	scripts/import_milhdbk5h_public_metals.py
Review status	Checked

Field	Value
Review scope	Checked official DLA document identity, Distribution Statement A, PDF hash, table/page location, alloy/condition/form/size scope, basis semantics, and SI conversions.
Notes	Historical reference only; design release is explicitly disabled.
License ID	US-DOD-DISTRIBUTION-STATEMENT-A
License URL	https://www.dodcui.mil/Distribution-Statements/
Attribution	U.S. Department of Defense

Material Condition

Field	Value
Condition	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm
Temper	STA (1000 degF/8 h)
Heat treatment	solution treated and aged 8 hours at 1000 degF per the source table
Product form	sheet
Thickness / diameter range	<=0.0748 in (1.9 mm), subset of the <=0.125 in table column
Test direction	L and LT
Processing route	wrought beta titanium-alloy sheet
Temperature range	21 ... 21 degC
Notes	Room-temperature historical handbook values. Applicability is limited to the exact alloy, temper/condition, product form, size band, material axis, statistical basis, and specification identified by the cited table. Historical reference only; confirm the current procurement specification and material test report.

Properties

Physical

Property	Value	Unit	Type	Applies to
Density	4761	kg/m^3	Historical Nominal	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column

Mechanical

Property	Value	Unit	Type	Applies to
Ultimate tensile strength, L	999.74	MPa	Historical Public Release Table Value	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column; L direction
Tensile yield strength, L	965.266	MPa	Historical Public Release Table Value	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column; L direction
Ultimate tensile strength, LT	999.74	MPa	Historical Public Release Table Value	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column; LT direction
Tensile yield strength, LT	965.266	MPa	Historical Public Release Table Value	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column; LT direction
Compressive yield strength, L	958.371	MPa	Historical Public Release Table Value	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column; L direction
Compressive yield strength, LT	992.845	MPa	Historical Public Release Table Value	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column; LT direction
Ultimate shear strength	634.318	MPa	Historical Public Release Table Value	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column
Elongation, L	7	%	Historical Public Release Table Value	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column; L direction
Elongation, LT	7	%	Historical Public Release Table Value	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column; LT direction

Property	Value	Unit	Type	Applies to
Young's modulus, L	104.8	GPa	Historical Nominal	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column; L direction
Young's modulus, LT	108.248	GPa	Historical Nominal	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column; LT direction
Compression modulus, L	105.49	GPa	Historical Nominal	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column; L direction
Compression modulus, LT	110.316	GPa	Historical Nominal	Ti-15V-3Cr-3Sn-3Al; solution treated and aged; sheet; <=1.9 mm; S-basis, <=0.125 in STA 1000 degF/8 h column; LT direction

Engineering note: seed solid-material values are reference values only. Verify against the project material specification or supplier data sheet before release.